

Aluminium alloy EN AB-42000

Chemical designation:

EN AB-AlSi7Mg

Swedish standard:

Type 4244, [1], [2]

Chemical composition¹:

	Min %	Max %
Si	6,5	7,5
Fe	-	0,45
Cu	-	0,15
Mn	-	0,35
Mg	0,25	0,65
Cr	-	-
Ni	-	0,15
Zn	-	0,15
Pb	-	0,094
Sn	-	0,05
Ti	-	0,20

Others each max 0,05%
and total max 0,15%

General description of properties:

Hypoeutectic alloy with good castability properties. Good machinability, good weldability and high resistance to chemical attack.

Suitable applications:

For complicated pressure-tight castings subject to fatigue loading. Good resistance to corrosion and high strength after heat treatment

Heat treatment:

Solution heat treated at 520-530°C for 3-6 hours followed by quenching in water and artificial ageing at 150-175°C for 15-5 hours

Casting characteristics, S-Sand cast, K-Chill cast²:

Solidification range, °C, about	Casting temperature °C, about	Fluidity	Resistance to hot tearing	Shrinkage %, about	Pressure tightness
620-570	700-750	Good	Excellent	S: 1-1,2 K: 0,8-1	Good

Mechanical properties of separately untreated cast test bars²:

Tensile strength, R _m , MPa, min.	Proof stress R _{p0,2} , MPa, min.	Elongation A ₅₀ , %, min.	Brinell hardness HBS, min.
S: 140 K: 170	S: 80 K: 90	S: 2 K: 2,5	S: 50 K: 55

Mechanical and physical properties²:

Density kg/dm ³	Strength	Machinability	Weldability	Resistance to corrosion
2,65	Good	Good	Good	Good/Satisfact.
Decorative anodizing	Ability to be polished	Linear thermal expansion 293-373°K, °K ⁻¹	Electrical conductivity MS/m	Thermal conductivity W/m°K
Poor	Satisfact.	22 x 10 ⁻⁶	19 – 25	150 - 170